

[Type here]

# PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

## FLOORCOAT

### Description and Application

#### CATEGORY

Floor Coating

#### DESCRIPTION

FloorCoat Alkyd Polyurethane Floor Paint has been formulated for domestic and light industrial concrete floors. It dries to a tough durable finish with excellent adhesion. Paintcor's FloorCoat is not recommended for exterior use. It is supplied in a range of standard colours and has a medium gloss finish.

#### FEATURES

- Tough, durable, thin film floor paint system.
- Designed to be resistant to most household chemicals.
- Single pack. (requires no catalyst)
- Excellent stain resistance and easy to clean.

#### AREAS OF USE

- Interior concrete floors
- Interior wooden floors
- Interior porous tile floors

#### SURFACE PREPARATION AND APPLICATION METHOD

##### NEW OR UNPAINTED FLOORS

1. Ensure floor is cured with a moisture level below 15%.
2. Clean floor and degrease if necessary.
3. Acid wash floor with undiluted hydrochloric acid (pool acid) and rinse well (immediately) with fresh water. There must be no acid left on the floor. Allow to dry.
4. Apply the first coat of FloorCoat DILUTED with 10% mineral turpentine (100ml turpentine in 1L tin FloorCoat or 500ml turpentine in 5L tin FloorCoat. Allow 6 hours to dry @ 25°C.
5. Apply a second coat of UNDILUTED FloorCoat. Allow to dry.

**Paintcor cc**  
Reg No: CK 86/19456/23  
VAT No: 4830119311

**Members:** G. Williams, G. Adendorff  
W. Williams

**Head office:** 1494 Mailship  
street, Laser Park, Honeydew, 2040  
**Postal Address:** P.O. Box 917,  
Northriding, 2162  
**RSA**

**Email**  
sales@paintcor.co.za

**Website**  
www.paintcor.co.za

**Tel:** 011 794 2885  
**Fax no:** 011 794 6955

**Emergency Numbers**  
+27(0) 79 526 1565  
+27(0) 84 305 5636



**SABS**  
ISO 9001 CERTIFIED



[Type here]

# PAINTCOR

SUPREME QUALITY *Since 1986*

## **PREVIOUSLY PAINTED FLOORS**

**NOTE:** This product is not compatible with all floor coatings e.g. FloorCoat cannot be used over an epoxy floor coating. If you are in any doubt as to Paintcor FloorCoat compatibility please contact our Technical Support Team on (011) 794-4599.

1. Remove any loose or peeling paint. If unpainted concrete areas are exposed, treat as for new floors above.
2. Degrease floor if necessary. Rinse well and allow to dry.
3. Sand existing floor paint to a clean matt finish. Remove sanding dust. Ensure floor is dry.
4. Prime expose concrete with 1 coat of Paintcor's FloorCoat DILUTED with 10% mineral turpentine. Allow 6 hours to dry @ 25°C.
5. Apply 2 coats UNDILUTED FloorCoat. Allow to dry between coats.

## **APPLICATION EQUIPMENT**

Brush, Mohair roller or spray.

## **CLEANING EQUIPMENT**

Clean all equipment with mineral turpentine immediately after use.

## **STORAGE**

Keep stored in cool, dry conditions and away from children. Flammable product, keep away from open flame.