

PAINTCOR

SUPREME QUALITY *Since 1986*

2020 Revision

POOLCURE

Technical Specifications

Vehicle Type	2K Epoxy
Solvent	No Solvent
Enviro Rating	Flammable 3
Dilution / Thinning	This product is supplied ready for use.
Theoretical Spread Rate	8 m ² per litre per coat.
Apply with	Brush or Roller
Drying time	@ 25°C – 6 hours overcoat
Wash ability	Excellent
Elongation	N/A
Pigment	Pigmented to standard colours
Solids Volume	98 - 99%
Flexibility	Poor
Colour	Black, Blue, White
Finish	Gloss
Storage	Cool, dry place. Keep out of reach of children.
Over coating	Between Primer & Top coat: 6 hours @25°C Between top coats: 12 hours @25°C
Packaging	1L, 5L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Excellent
Impact Resistance	Excellent
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable
Catalyst Ratio	25.5gms Catalyst to 100gms Base
Recommended Dry Film	100 um per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Good
Appearance	Black, Blue or White

Note: Application directions must be strictly followed for this product to perform to its full potential. This product carries no guarantee once applied.

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sales@paintcor.co.za

Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 CERTIFIED

